


MOUSQUETON POIRE


Acier C 15 - Galvanisation électrolytique



Désignation	Rupture kg	A	B	Dimensions en mm			L	Poids kg
40	100	7	4.5	6.5	4.5	40	0.010	
50	120	8	5.5	7.5	5	50	0.016	
60	120	9	6.5	9	6	60	0.027	
70	180	10	8	9	7	70	0.044	
80	230	11	8.5	11	8	80	0.066	
90	250	13	9.5	15	9	90	0.092	
100	350	15	10.5	15	10	100	0.128	
120	450	18	12	17	11	120	0.184	
140	510	20	15	21	12	140	0.257	
160	600	23	17.5	30	13	160	0.353	
180	650	22	16.5	35	14	180	0.496	
200	700	26	17.5	45	15	200	0.615	

MOUSQUETON À VIS


Acier C 15 - Galvanisation électrolytique



Désignation	Rupture kg	A	B	Dimensions en mm			L	Poids kg
100	350	15	10.5	13	10	100	0.130	
120	500	18	12	16.5	11	120	0.186	

MOUSQUETON

Acier C 15 - Galvanisation électrolytique



Désignation	Rupture kN	C	D	L	Poids kg
100	22	20	10	102	0.138

MOUSQUETON À VERROUILLAGE

Acier C 15 - Galvanisation électrolytique



Désignation	Rupture kN	C	D	L	Poids kg
100	22	18	10	102	0.140

MAILLON RAPIDE PETITE OUVERTURE


Acier Fe 360 B - Galvanisation électrolytique



Désignation	Charge rupture (kg)	A	B	C	S	L	Poids kg
3.5	500	10	30	3.5	7	0.010	
04	900	12	33	4	8	0.010	
05	1 400	13	40	5	9	0.020	
06	2 000	15	46	6	11	0.030	
07	2 750	16	52	7	12.5	0.060	
08	3 500	17.5	58	8	14	0.080	
09	4 500	19	62	9	15	0.110	
10	5 500	20.5	69	10	17	0.150	
12	7 500	23.5	80.5	12	19	0.230	

MAILLON RAPIDE OVALE GRANDE OUVERTURE

Acier - Galvanisation électrolytique



Désignation	Charge rupture (kg)	A	B	C	L	Poids kg
04	800	11.5	4	11.5	45	0.015
05	1 250	13	5	13	52	0.025
06	1 750	14.5	6	14.5	58.5	0.042
07	2 500	16	7	16	65	0.060
08	3 200	17.5	8	17.5	72	0.090

MAILLON RAPIDE TRIANGULAIRE

Acier - Galvanisation électrolytique



Désignation	Charge rupture (kg)	A	B	C	L	Poids kg
04	500	5.5	4	27.5	32	0.014
06	1 250	7.5	6	35	44	0.039
08	2 750	10	8	40	57	0.086
10	4 500	12	10	46	67	0.152
12	5 500	15	12	51	80	0.256
14	9 000	17	14	57	95	0.403
16	11 000	19	16	61	106	0.612